


# O`RINGS ENCAPSULADOS



Certificada ISO 9001/2008



	Rubber Temperature Range			
	FEP		PFA	
<b>Silicon</b>	-60° ~+205	-75° ? +400oF	-60° ~+260	-75.° ? +500oF
<b>Viton</b>	260 ~+205	-15° ? +400oF	-26° ~+205	-15.° ? +400oF
<b>EPDM</b>	-54° ~+149	-65° ~+300oF	-54° ~+149	-65° ~+300oF